



GP[®]1



GP[®]1 proprietary gas resistant damp proof membrane (DPM) is a multi-layer, low density polyethylene membrane, reinforced with a polypropylene reinforcing grid with an integral aluminium foil. GP[®]1 is specifically designed and manufactured to perform as a methane, carbon dioxide, radon, ground gas, air & moisture protection system.

Thickness	0.6 mm
Width	Various m
Length	Various m
Weight	370 g/m ²

TITANTECH[®]

For developers of brownfield and contaminated sites the TITANTECH[®] family of products represent a major step forward in safeguarding projects against gaseous and chemical contamination.

Handling

Roll weights can be in excess of 20 kg and hence appropriate care and equipment is required for unloading and handling.

Storage

Rolls of GP[®]1 should be stored on stable/level ground and stacked not more than five rolls high, with no other material stacked on top. The rolls can be stored outdoors when packaged, but should be protected from exposure to UV.

Installation

GP[®]1 should be installed in accordance with the product installation guidelines, and in accordance with BS 8485:2015.





Feature	Characteristics	Test Method	GP ¹
Physical Properties	Thickness	EN 1849-2	0.6 mm
	Thickness - between Scrim	BS EN ISO 9863-1:2016	0.4 mm
	Width	EN 1849-2	Various m
	Length	EN 1849-2	Various m
	Weight	EN 1849-2	370 g/m ²
Hydraulic Press	Water Column	EN 20811	> 300
	Resistance to Water Penetration	EN 13967, EN 1928	Pass
	Water Tightness	EN 11296, EN 1367, EN 1928	Pass
Mechanical Properties	Resistance to Static Load	EN 12730-B	20 kg
	Tensile Strength (MD)	EN 12311-1	600 N/50mm
	Tensile Strength (CMD)	EN 12311-1	480 N/50mm
	Tensile Elongation (MD)	EN 12310-1	20%
	Tensile Elongation (CMD)	EN 12310-1	20%
	Puncture Resistance	EN 12236	1.25 kN
	Resistance to Tearing (Nail Shank) MD	EN 12310-1	330 N
	Resistance to Tearing (Nail Shank) CMD	EN 12310-1	400 N
Durability and Chemical Resistance	Transmission Rate of Volatile Liquids - Diesel	ISO 6179:2010 (B)	0.246 g/m ² /h
	Transmission Rate of Volatile Liquids - Xylene	ISO 6179:2010 (B)	0.571 g/m ² /h
	Transmission Rate of Volatile Liquids - Toluene	ISO 6179:2010 (B)	0.583 g/m ² /h
	Transmission Rate of Volatile Liquids - Petrol	ISO 6179:2010 (B)	0.135 g/m ² /h
Gas Permeability	Methane Permeability	BS EN ISO 15105-1	< 0.09 ml/m ² /day/atm
	Carbon Dioxide Permeability	BS EN ISO 15105-1	< 0.09 ml/m ² /day/atm
	Radon Permeability	K124/02/95	8.0 x 10 ⁻¹⁵ m ² /s
Compliance and Certification	CE Mark - EN13967:2012 (A1 2017)		
	NHBC Standards Compliant		
	Conforms to BS 8485:2015 + A1 2019		
	BBA Certified - Certificate No. 20/5728		

JUTA UK

Please contact JUTA UK Directly for more information on GP¹

Jointing and Sealing

It is recommended GP¹ be heat welded where possible, with welding carried out by competent personnel with suitable qualifications in accordance with best practice, and guidance contained within BS 8485:2015.

Accessory Products

- GP¹ Starter Band
- GP¹ Tape
- GP¹ Self Adhesive Membrane
- GP¹ Primer
- GP¹ Top Hats and Preformed Corners
- GP¹ Protection Fleece
- GP¹ Void Vent (24/40mm)