GROUND GAS PROTECTION GP'1 SAM TECHNICAL DATA

JUTA



GPI SAM

GP®1 SAM, gas protection self adhesive membrane, is a bituminous gas proof and water proof sheet, composed of self-adhesive SBS polymer modified bitumen incorporating GP®1 with an upper surface finish of black reinforced LDPE, and a lower surface finish of siliconized release film. GP®1 SAM is used for the gas/ waterproofing of underground structures where harmful ground gasses are anticipated, and as a self adhesive accessory to GP®1.

Thickness Width Length Weight

BBA

CE CK

1.2 mm 0.9 m or 0.3 m 20 m 1100 g/m²

TITANTECH[®]

For developers of brownfield and contaminated sites the TITANTECH[®] family of products represent a major step forward in safeguarding projects against gaseous and chemical contamination.

Handling

Roll weights can be in excess of 20 kg (approx 33 kg/roll) and hence appropriate care and equipment is required for unloading and handling. This product is non-toxic nor flammable.

Storage

Rolls of GP[®]1 SAM should be stored on in a cool, dry place, and be protected from exposure to rain, sun, heat and cold temperatures prior to installation. Exposure to sunlight for extended period of time could cause difficulty with removal of the release film.

Juta.co.uk

GROUND GAS PROTECTION GP°1 SAM TECHNICAL DATA SHEET



Feature	Characteristics	Test Method	GP®1 SAM
Physical Properties	Thickness	EN 1849-2	1.2 mm
	Width	EN 1849-2	0.9 or 0.3 m
	Length	EN 1849-2	20 m
	Weight	EN 1849-2	1100 g/m ²
Hydraulic Press	Water Tightness	EN 1928	Pass
	Water Vapour Transmission	EN 1931	0.013 g/m²/day
Mechanical Properties	Tensile Strength (MD/CMD)	EN 12311-2 (A)	500 N/50mm
	Elongation (MD/CMD)	EN 12311-2 (A)	> 12 %
	Resistance to Static Load	EN 12370	20 kg
	Joint Strength	EN 12317-2	> 30 N
	Durability and Water Tightness (Ageing and Chemicals) 60 kPa	EN 1847	Pass
	Resistance to Nail Tear (MD/CMD)	EN 12310-1	> 300 N
	Resistance to Fire	EN 13501	F Euro Class
Gas Permeability	Methane Permeability	EN ISO 15105-1	< 0.68 ml/m²/day/atm
	Carbon Dioxide Permeability	EN ISO 15105-1	< 2.81 ml/m²/day/atm
	Radon Permeability	K124/02/95	8.0 x 10 ⁻¹⁵ m ² /S
Compliance and Certification	CE Mark - EN13967:2012 + A1:2017 Type (A/T)		
	BS 8485:2015 Compliant (Methane and Carbon Dioxide Barrier)		

JUTA UK

Please contact JUTA UK Directly for more information on GP®1 SAM

Installation

GP®1 SAM should be installed in accordance with the product installation guidelines, and in accordance with BS 8485:2015, and/or BS 8102:2009.

It is recommended that GP®1 SAM is not applied in temperatures below 10°C, in colder weather the material can be warmed slightly to aid adhesion.

Accessory Products

• GP[®] Primer

- GP[®] Protection Fleece
- GP® Protection Board

Juta.co.uk